



PRODUCT	<b>Polyroof Mono</b>
MISSION	One component polyurethane liquid waterproofing
CHARACTERISTICS	<p>Polyroof Mono is a one component waterproofing liquid coating and ready to use. The product, reacting with the moisture of the environment, once hardened, creates a continuous waterproofing coating without joints, elastic and walkable. This can be used to waterproof balconies, terraces, roofing with complex geometry.</p> <p>Polyroof Mono is also resistant to water pooling and has a good resistance to UV rays (its aromatic composition can cause a mild light change of colour without compromising the technical characteristics). Once hardened, the product can be painted with Polytop to obtain a higher aesthetic result. Finally, tiles can be applied directly on the Polyroof Mono; in this case the last coats must be soaked with quartz sand.</p>
APPEARANCE	Medium viscosity colored liquid

**CHARACTERISTICS OF THE LIQUID PRODUCT**

CHARACTERISTICS	VALUE	TOLERANCE	U.M.
Specific weight	1,60	± 0,05	Kg/dm <sup>3</sup>
Dry residue	90	± 1	%
Viscosity at 20° C	7500	± 500	mPa.s

**APPLICATION INSTRUCTIONS**

TOOLS	THINNING	TYPE OF THINNER	TOOL CLEANING
Roller	Ready to use		DIL A1
Brush	Ready to use		DIL A1
Spray	Ready to use or MAX 5 %	DIL A1	DIL A1

LAYING SURFACE	<p>The cement laying surface must be clean, free of oils and dust; loose parts and possible soluble salts must be removed before the application. To prevent tearing of the contact surface during the catalysis, by the resin, the compression resistance must be at least 25 N/mm<sup>2</sup> and the traction resistance 1,5 N/mm<sup>2</sup>. In case the humidity of the substrate is equal or higher than 3%, before carrying out a resining cycle with Polyroof mono, it is necessary to lay a chemical barrier such as Epobase FU14.</p> <p>It is always recommended to make a mechanic treatment to remove inconsistent parts and improve the roughness of the laying surface, increasing its adhesiveness. Afterwards, it's advisable to apply a primer according to the state of laying surface (consult the Casali S.p.A. Technical Department).</p>
----------------	------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

CONSUMPTION	As a non-reinforced layer: 1.2-1.7 kg/ m <sup>2</sup> in two coats
-------------	--------------------------------------------------------------------





	As a reinforced system: 1.4-2 Kg/m <sup>2</sup> in two coats As waterproofing under tiles: 2.2Kg/ m <sup>2</sup> in two coats with the use of reinforcement and quartz powder 0.3-0.5
--	------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

<b>APPLICATION INSTRUCTIONS</b>	Homogenize before use. Environmental and deck temperature limit during application: MIN 10° C - MAX 30° C
---------------------------------	--------------------------------------------------------------------------------------------------------------

<b>HARDENING AT 22° C AND 50 % U.R.</b>	Pot life: 30' / 45' To touch: 7-9 h Interval between coatings: within 24 h  The timing indicated above are intended for standard laboratory conditions. Drying times are strongly affected by weather conditions; high temperatures and direct sunlight reduce the drying times; low temperatures and high humidity increase the drying times. In the wintertime the product should be laid in the middle of the day when it is warmer. Ensure that the previous layer has dried properly before applying the next layer.
-----------------------------------------	---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

<b>CHARACTERISTICS OF THE DRY PRODUCT</b>			
<b>CHARACTERISTICS</b>	<b>VALUE</b>	<b>TOLERANCE</b>	<b>U.M.</b>
Breaking load	4,00	± 0,05	MPa
Elongation at break	>450	± 50	%
Shore A hardness	70	± 2	
Adhesion on CLS	2,2	± 0,05	MPa
Permeability to water vapour	20		g/mq day

<b>PACKAGING INSTRUCTIONS</b>	<b>COLOURS AVAILABLE</b> Grey (RAL 7001) - others on request	<b>PACKAGING</b> 25 Kg
<b>STORAGE INSTRUCTIONS</b>	<b>STORAGE TEMPERATURE</b> MIN 10° C – MAX 35° C	<b>STABILITY IN THE ORIGINAL PACKAGE</b> 6 months
<b>SAFETY STANDARDS</b>	Please read the safety data sheet carefully before using this product.	

